

NTC thermistors for temperature measurement

Glass-encapsulated sensors,
standard type

Series/Type: B57550G, B57550G1

The following products presented in this data sheet are being withdrawn.

Ordering Code	Substitute Product	Date of Withdrawal	Deadline Last Orders	Last Shipments
B57550G0145*	B57550G1104*	2012-03-23	2012-06-28	2012-09-28
B57550G0234*	B57550G1104*	2012-03-23	2012-06-28	2012-09-28

For further information please contact your nearest EPCOS sales office, which will also support you in selecting a suitable substitute. The addresses of our worldwide sales network are presented at www.epcos.com/sales.

© EPCOS AG 2015. Reproduction, publication and dissemination of this publication, enclosures hereto and the information contained therein without EPCOS' prior express consent is prohibited.

EPCOS AG is a TDK Group Company.

Applications

- Temperature measurement

Features

- Glass-encapsulated, heat-resistive and highly stable
- For temperature measurement up to 300 °C
- Very short response time
- Small dimensions
- Leads: dumet wires (copper-clad FeNi)


Options

- Leads: nickel-plated dumet wires
- Alternative dimensions available on request

Delivery mode

Bulk

Dimensional drawing



Dimensions in mm

General technical data

Climatic category	(IEC 60068-1)		55/300/56	
Max. power	(at 25 °C)	P_{25}	32	mW
Resistance tolerance		$\Delta R_R/R_R$	$\pm 1, \pm 2, \pm 3$	%
Rated temperature		T_R	25	°C
Dissipation factor	(in air)	δ_{th}	approx. 0.75	mW/K
Thermal cooling time constant	(in air)	τ_c	approx. 7	s
Heat capacity		C_{th}	approx. 5	mJ/K

Electrical specification and ordering codes

R ₂₅ Ω	No. of R/T characteristic	B _{25/85} K	B _{0/100} K	B _{25/100} K	Ordering code
2 k	8401	3420	3390 ±1%	3436	B57550G0202+000
2 k	8401	3420	3390 ±1%	3436	B57550G0202+002
5 k	8402	3480	3450 ±1%	3497	B57550G0502+000
5 k	8402	3480	3450 ±1%	3497	B57550G0502+002
10 k	7003	3612	3586	3625 ±1%	B57550G1103+005
10 k	7003	3612	3586	3625 ±1%	B57550G1103+007
10 k	8307	3478	3450	3492 ±1%	B57550G1103+000
10 k	8307	3478	3450	3492 ±1%	B57550G1103+002
20 k	8415	3992	3970 ±1%	4006	B57550G0203+000
20 k	8415	3992	3970 ±1%	4006	B57550G0203+002
30 k	7002	3973	3944	3988 ±1%	B57550G1303+005
30 k	7002	3973	3944	3988 ±1%	B57550G1303+007
50 k	8403	3992	3970 ±1%	4006	B57550G0503+000
50 k	8403	3992	3970 ±1%	4006	B57550G0503+002
100 k	8304	4072	4036	4092 ±1%	B57550G1104+000
100 k	8304	4072	4036	4092 ±1%	B57550G1104+002
230 k	8405	4240	4537 ±1% ¹⁾	4264	B57550G0234+000
230 k	8405	4240	4537 ±1% ¹⁾	4264	B57550G0234+002
1400 k	8406	4557	5133 ±2% ²⁾	4581	B57550G0145+000
1400 k	8406	4557	5133 ±2% ²⁾	4581	B57550G0145+002

+ = Resistance tolerance

F = ±1%

G = ±2%

H = ±3%

The last three digits of the ordering code denote:

000 and 005 = dumet wires

002 and 007 = nickel-plated wires

1) B_{100/200}

2) B_{200/300}

Temperature measurement	B57550G, B57550G1
Glass-encapsulated sensors	G550/G1550

Reliability data

Test	Standard	Test conditions	$\Delta R_{25}/R_{25}$ (typical)	Remarks
Storage in dry heat	IEC 60068-2-2	Storage at upper category temperature T: 300 °C t: 1000 h	< 3%	No visible damage
Storage in damp heat, steady state	IEC 60068-2-67	Temperature of air: 85 °C Relative humidity of air: 85% Duration: 56 days	< 2%	No visible damage
Rapid temperature cycling	IEC 60068-2-14	Lower test temperature: –55 °C Upper test temperature: 200 °C Number of cycles: 1000	< 2%	No visible damage

R/T characteristics

R/T No.	7002		7003		8304	
T (°C)	B _{25/100} = 3988 K		B _{25/100} = 3625 K		B _{25/100} = 4092 K	
	R _T /R ₂₅	α (%/K)	R _T /R ₂₅	α (%/K)	R _T /R ₂₅	α (%/K)
-55.0	96.33	7.4	63.225	6.7	100.11	7.4
-50.0	66.866	7.2	45.46	6.5	69.56	7.2
-45.0	47.037	6.9	33.07	6.3	48.945	6.9
-40.0	33.508	6.7	24.324	6.0	34.853	6.7
-35.0	24.156	6.4	18.081	5.8	25.102	6.5
-30.0	17.613	6.2	13.575	5.6	18.275	6.2
-25.0	12.98	6.0	10.29	5.4	13.443	6.0
-20.0	9.6643	5.8	7.8716	5.3	9.9853	5.9
-15.0	7.2656	5.6	6.0739	5.1	7.4867	5.7
-10.0	5.5129	5.4	4.7258	4.9	5.6636	5.5
-5.0	4.22	5.3	3.7062	4.8	4.3212	5.3
0.0	3.2575	5.1	2.9287	4.6	3.324	5.2
5.0	2.5348	4.9	2.3311	4.5	2.5769	5.0
10.0	1.9876	4.8	1.8684	4.4	2.0127	4.9
15.0	1.5699	4.6	1.5075	4.2	1.5834	4.7
20.0	1.2488	4.5	1.224	4.1	1.2542	4.6
25.0	1.0000	4.4	1.0000	4.0	1.0000	4.5
30.0	0.80594	4.3	0.82176	3.9	0.80239	4.3
35.0	0.65355	4.1	0.67909	3.8	0.64776	4.2
40.0	0.53312	4.0	0.56422	3.7	0.52598	4.1
45.0	0.43735	3.9	0.47122	3.6	0.4295	4.0
50.0	0.36074	3.8	0.3955	3.5	0.35262	3.9
55.0	0.29911	3.7	0.33355	3.4	0.291	3.8
60.0	0.24925	3.6	0.2826	3.3	0.24136	3.7
65.0	0.20872	3.5	0.24049	3.2	0.20114	3.6
70.0	0.17558	3.4	0.20553	3.1	0.16841	3.5
75.0	0.14837	3.3	0.17637	3.0	0.14164	3.4
80.0	0.12592	3.2	0.15195	2.9	0.11963	3.3
85.0	0.10731	3.2	0.13141	2.9	0.10147	3.3
90.0	0.091816	3.1	0.11406	2.8	0.086407	3.2
95.0	0.078862	3.0	0.099352	2.7	0.073867	3.1
100.0	0.067988	2.9	0.086837	2.7	0.063383	3.0
105.0	0.058824	2.9	0.076149	2.6	0.054584	3.0
110.0	0.051071	2.8	0.066989	2.5	0.04717	2.9
115.0	0.044489	2.7	0.059112	2.5	0.040901	2.8
120.0	0.03888	2.7	0.052316	2.4	0.035581	2.8
125.0	0.034084	2.6	0.046433	2.4	0.03105	2.7
130.0	0.02997	2.5	0.041327	2.3	0.027179	2.6
135.0	0.02643	2.5	0.03688	2.3	0.023861	2.6
140.0	0.023373	2.4	0.032998	2.2	0.021008	2.5
145.0	0.020727	2.4	0.029598	2.2	0.018548	2.5
150.0	0.018429	2.3	0.026612	2.1	0.016419	2.4
155.0	0.016427	2.3	0.023984	2.1	0.014573	2.4

Temperature measurement
B57550G, B57550G1
Glass-encapsulated sensors
G550/G1550

R/T No.	7002		7003		8304	
T (°C)	$B_{25/100} = 3988 \text{ K}$		$B_{25/100} = 3625 \text{ K}$		$B_{25/100} = 4092 \text{ K}$	
	R_T/R_{25}	$\alpha \text{ (%/K)}$	R_T/R_{25}	$\alpha \text{ (%/K)}$	R_T/R_{25}	$\alpha \text{ (%/K)}$
160.0	0.014679	2.2	0.021665	2.0	0.012967	2.3
165.0	0.013149	2.2	0.019613	2.0	0.011566	2.3
170.0	0.011806	2.1	0.017793	1.9	0.010341	2.2
175.0	0.010623	2.1	0.016176	1.9	0.0092664	2.2
180.0	0.0095804	2.0	0.014735	1.8	0.0083224	2.1
185.0	0.0086582	2.0	0.013448	1.8	0.0074907	2.1
190.0	0.0078408	2.0	0.012297	1.8	0.0067564	2.0
195.0	0.0071148	1.9	0.011265	1.7	0.0061064	2.0
200.0	0.0064685	1.9	0.010338	1.7	0.0055299	2.0
205.0	0.005892	1.8	0.009504	1.7	0.0050175	1.9
210.0	0.0053767	1.8	0.0087516	1.6	0.0045611	1.9
215.0	0.0049152	1.8	0.0080718	1.6	0.0041537	1.9
220.0	0.0045011	1.7	0.0074567	1.6	0.0037895	1.8
225.0	0.0041287	1.7	0.0068989	1.5	0.0034631	1.8
230.0	0.0037934	1.7	0.0063925	1.5	0.0031701	1.8
235.0	0.0034908	1.6	0.0059318	1.5	0.0029067	1.7
240.0	0.0032173	1.6	0.005512	1.5	0.0026693	1.7
245.0	0.0029697	1.6	0.005129	1.4	0.0024551	1.7
250.0	0.0027451	1.6	0.004779	1.4	0.0022615	1.6
255.0	0.0025412	1.5	0.0044586	1.4	0.0020862	1.6
260.0	0.0023556	1.5	0.004165	1.4	0.0019273	1.6
265.0	0.0021865	1.5	0.0038955	1.3	0.0017829	1.5
270.0	0.0020323	1.5	0.0036478	1.3	0.0016516	1.5
275.0	0.0018913	1.4	0.0034199	1.3	0.0015319	1.5
280.0	0.0017623	1.4	0.0032098	1.3	0.0014228	1.5
285.0	0.0016441	1.4	0.003016	1.2	0.0013231	1.4
290.0	0.0015357	1.4	0.002837	1.2	0.0012319	1.4
295.0	0.001436	1.3	0.0026714	1.2	0.0011483	1.4
300.0	0.0013444	1.3	0.002518	1.2	0.0010716	1.4

R/T characteristics

R/T No.	8307		8401		8402	
T (°C)	B _{25/100} = 3492 K		B _{0/100} = 3390 K		B _{0/100} = 3450 K	
	R _T /R ₂₅	α (%/K)	R _T /R ₂₅	α (%/K)	R _T /R ₂₅	α (%/K)
-55.0	52.624	6.4	48.237	6.2	51.991	6.4
-50.0	38.452	6.2	35.488	6.0	37.989	6.2
-45.0	28.401	6.0	26.39	5.8	28.07	5.9
-40.0	21.194	5.8	19.825	5.6	20.96	5.7
-35.0	15.972	5.6	15.037	5.4	15.809	5.5
-30.0	12.149	5.4	11.511	5.3	12.037	5.4
-25.0	9.3246	5.2	8.8893	5.1	9.2484	5.2
-20.0	7.2181	5.0	6.9218	4.9	7.1668	5.0
-15.0	5.6332	4.9	5.4326	4.8	5.5993	4.9
-10.0	4.4308	4.7	4.2961	4.6	4.4087	4.7
-5.0	3.5112	4.6	3.422	4.5	3.4971	4.6
0.0	2.8024	4.4	2.7445	4.3	2.7936	4.4
5.0	2.252	4.3	2.2158	4.2	2.2468	4.3
10.0	1.8216	4.2	1.8002	4.1	1.8187	4.2
15.0	1.4827	4.1	1.4714	4.0	1.4813	4.0
20.0	1.2142	3.9	1.2097	3.9	1.2136	3.9
25.0	1.0000	3.8	1.0000	3.8	1.0000	3.8
30.0	0.82818	3.7	0.8311	3.6	0.82845	3.7
35.0	0.68954	3.6	0.69427	3.5	0.68991	3.6
40.0	0.57703	3.5	0.58282	3.5	0.57742	3.5
45.0	0.48525	3.4	0.49158	3.4	0.4856	3.4
50.0	0.41	3.3	0.41652	3.3	0.41026	3.3
55.0	0.34798	3.2	0.35446	3.2	0.34816	3.2
60.0	0.29663	3.2	0.30292	3.1	0.29673	3.2
65.0	0.25392	3.1	0.25994	3.0	0.25393	3.1
70.0	0.21824	3.0	0.22392	2.9	0.21817	3.0
75.0	0.1883	2.9	0.19363	2.9	0.18816	2.9
80.0	0.16307	2.8	0.16805	2.8	0.16288	2.8
85.0	0.14174	2.8	0.14636	2.7	0.1415	2.8
90.0	0.12362	2.7	0.1279	2.7	0.12335	2.7
95.0	0.10818	2.6	0.11214	2.6	0.10788	2.6
100.0	0.094973	2.6	0.098635	2.5	0.094659	2.6
105.0	0.08364	2.5	0.087023	2.5	0.083313	2.5
110.0	0.073881	2.5	0.077007	2.4	0.073547	2.5
115.0	0.06545	2.4	0.06834	2.4	0.065114	2.4
120.0	0.058144	2.3	0.060818	2.3	0.05781	2.4
125.0	0.051794	2.3	0.05427	2.3	0.051464	2.3
130.0	0.046259	2.2	0.048554	2.2	0.045936	2.2
135.0	0.04142	2.2	0.043551	2.2	0.041106	2.2
140.0	0.037179	2.1	0.039159	2.1	0.036875	2.1
145.0	0.033451	2.1	0.035294	2.1	0.033159	2.1
150.0	0.030166	2.0	0.031885	2.0	0.029886	2.1
155.0	0.027264	2.0	0.02887	2.0	0.026998	2.0

Temperature measurement
B57550G, B57550G1
Glass-encapsulated sensors
G550/G1550

R/T No.	8307		8401		8402	
T (°C)	$B_{25/100} = 3492 \text{ K}$		$B_{0/100} = 3390 \text{ K}$		$B_{0/100} = 3450 \text{ K}$	
	R_T/R_{25}	$\alpha \text{ (%/K)}$	R_T/R_{25}	$\alpha \text{ (%/K)}$	R_T/R_{25}	$\alpha \text{ (%/K)}$
160.0	0.024694	2.0	0.026197	1.9	0.024442	2.0
165.0	0.022414	1.9	0.023822	1.9	0.022175	1.9
170.0	0.020385	1.9	0.021707	1.8	0.02016	1.9
175.0	0.018577	1.8	0.01982	1.8	0.018365	1.8
180.0	0.016961	1.8	0.018132	1.8	0.016762	1.8
185.0	0.015514	1.8	0.016619	1.7	0.015328	1.8
190.0	0.014216	1.7	0.01526	1.7	0.014043	1.7
195.0	0.013049	1.7	0.014038	1.7	0.012888	1.7
200.0	0.011999	1.7	0.012936	1.6	0.011849	1.7
205.0	0.011051	1.6	0.011941	1.6	0.010913	1.6
210.0	0.010194	1.6	0.011041	1.6	0.010067	1.6
215.0	0.0094181	1.6	0.010225	1.5	0.0093013	1.6
220.0	0.0087144	1.5	0.0094848	1.5	0.0086075	1.5
225.0	0.0080751	1.5	0.0088113	1.5	0.0079777	1.5
230.0	0.0074933	1.5	0.0081978	1.4	0.007405	1.5
235.0	0.0069631	1.5	0.0076382	1.4	0.0068833	1.4
240.0	0.0064791	1.4	0.0071268	1.4	0.0064075	1.4
245.0	0.0060366	1.4	0.006659	1.3	0.0059728	1.4
250.0	0.0056316	1.4	0.0062302	1.3	0.0055751	1.4
255.0	0.0052602	1.4	0.0058368	1.3	0.0052107	1.3
260.0	0.0049193	1.3	0.0054753	1.3	0.0048764	1.3
265.0	0.0046059	1.3	0.0051426	1.2	0.0045692	1.3
270.0	0.0043173	1.3	0.004836	1.2	0.0042866	1.3
275.0	0.0040514	1.3	0.0045532	1.2	0.0040263	1.2
280.0	0.003806	1.2	0.004292	1.2	0.0037862	1.2
285.0	0.0035793	1.2	0.0040504	1.1	0.0035645	1.2
290.0	0.0033696	1.2	0.0038266	1.1	0.0033595	1.2
295.0	0.0031753	1.2	0.0036192	1.1	0.0031697	1.2
300.0	0.0029952	1.2	0.0034267	1.1	0.0029938	1.1

R/T characteristics

R/T No.	8403		8405		8406	
T (°C)	B _{0/100} = 3970 K		B _{100/200} = 4537 K		B _{200/300} = 5133 K	
	R _T /R ₂₅	α (%/K)	R _T /R ₂₅	α (%/K)	R _T /R ₂₅	α (%/K)
-55.0	103.29	7.6	122.12	7.8	183.3	8.5
-50.0	71.079	7.3	83.306	7.5	120.69	8.2
-45.0	49.619	7.1	57.62	7.2	80.721	7.9
-40.0	35.108	6.8	40.378	7.0	54.792	7.6
-35.0	25.158	6.5	28.647	6.7	37.713	7.3
-30.0	18.245	6.3	20.563	6.5	26.301	7.1
-25.0	13.383	6.1	14.925	6.3	18.571	6.8
-20.0	9.9221	5.9	10.947	6.1	13.269	6.6
-15.0	7.4316	5.7	8.1101	5.9	9.5865	6.4
-10.0	5.6202	5.5	6.0655	5.7	6.9997	6.2
-5.0	4.2894	5.3	4.5776	5.5	5.1625	6.0
0.0	3.3024	5.2	3.4845	5.4	3.844	5.8
5.0	2.5607	5.0	2.6743	5.2	2.8884	5.6
10.0	2.0017	4.8	2.0686	5.1	2.1892	5.5
15.0	1.5768	4.7	1.6121	4.9	1.673	5.3
20.0	1.2513	4.6	1.2654	4.8	1.2886	5.1
25.0	1.0000	4.4	1.0000	4.6	1.0000	5.0
30.0	0.80451	4.3	0.79548	4.5	0.78164	4.9
35.0	0.65139	4.2	0.63677	4.4	0.61516	4.7
40.0	0.53064	4.0	0.51279	4.3	0.48734	4.6
45.0	0.43481	3.9	0.41534	4.2	0.38851	4.5
50.0	0.35828	3.8	0.33828	4.1	0.3116	4.4
55.0	0.29681	3.7	0.27698	3.9	0.25136	4.2
60.0	0.24715	3.6	0.22795	3.8	0.2039	4.1
65.0	0.20682	3.5	0.18853	3.7	0.16629	4.0
70.0	0.17389	3.4	0.15666	3.7	0.1363	3.9
75.0	0.14687	3.3	0.13077	3.6	0.11228	3.8
80.0	0.12459	3.2	0.10964	3.5	0.092932	3.7
85.0	0.10614	3.2	0.092319	3.4	0.077268	3.6
90.0	0.09078	3.1	0.078049	3.3	0.064527	3.6
95.0	0.077949	3.0	0.066244	3.2	0.054116	3.5
100.0	0.067183	2.9	0.056439	3.2	0.045571	3.4
105.0	0.058113	2.9	0.048262	3.1	0.038526	3.3
110.0	0.050443	2.8	0.041416	3.0	0.032694	3.2
115.0	0.043932	2.7	0.035663	3.0	0.027847	3.2
120.0	0.038386	2.7	0.030811	2.9	0.023803	3.1
125.0	0.033645	2.6	0.026705	2.8	0.020416	3.0
130.0	0.029579	2.5	0.023218	2.8	0.017569	3.0
135.0	0.02608	2.5	0.020247	2.7	0.015167	2.9
140.0	0.02306	2.4	0.017707	2.7	0.013135	2.8
145.0	0.020446	2.4	0.01553	2.6	0.011409	2.8
150.0	0.018176	2.3	0.013658	2.5	0.0099385	2.7
155.0	0.016199	2.3	0.012043	2.5	0.0086821	2.7

Temperature measurement
B57550G, B57550G1
Glass-encapsulated sensors
G550/G1550

R/T No.	8403		8405		8406	
T (°C)	$B_{0/100} = 3970 \text{ K}$		$B_{100/200} = 4537 \text{ K}$		$B_{200/300} = 5133 \text{ K}$	
	R_T/R_{25}	$\alpha \text{ (%/K)}$	R_T/R_{25}	$\alpha \text{ (%/K)}$	R_T/R_{25}	$\alpha \text{ (%/K)}$
160.0	0.014473	2.2	0.010647	2.4	0.0076052	2.6
165.0	0.012962	2.2	0.009436	2.4	0.0066796	2.6
170.0	0.011636	2.1	0.0083831	2.3	0.0058817	2.5
175.0	0.010469	2.1	0.0074652	2.3	0.005192	2.5
180.0	0.0094395	2.0	0.006663	2.3	0.0045943	2.4
185.0	0.0085294	2.0	0.0059602	2.2	0.0040749	2.4
190.0	0.0077229	2.0	0.0053431	2.2	0.0036225	2.3
195.0	0.0070067	1.9	0.0047999	2.1	0.0032274	2.3
200.0	0.0063691	1.9	0.0043208	2.1	0.0028817	2.2
205.0	0.0058005	1.9	0.0038972	2.0	0.0025783	2.2
210.0	0.0052924	1.8	0.0035219	2.0	0.0023116	2.2
215.0	0.0048373	1.8	0.0031888	2.0	0.0020766	2.1
220.0	0.004429	1.7	0.0028925	1.9	0.0018691	2.1
225.0	0.004062	1.7	0.0026284	1.9	0.0016854	2.0
230.0	0.0037315	1.7	0.0023925	1.9	0.0015226	2.0
235.0	0.0034333	1.6	0.0021816	1.8	0.001378	2.0
240.0	0.0031639	1.6	0.0019925	1.8	0.0012492	1.9
245.0	0.00292	1.6	0.0018227	1.8	0.0011344	1.9
250.0	0.0026988	1.6	0.00167	1.7	0.0010318	1.9
255.0	0.002498	1.5	0.0015324	1.7	0.00094005	1.8
260.0	0.0023153	1.5	0.0014083	1.7	0.00085777	1.8
265.0	0.0021489	1.5	0.0012961	1.6	0.00078388	1.8
270.0	0.0019971	1.5	0.0011946	1.6	0.00071742	1.8
275.0	0.0018584	1.4	0.0011025	1.6	0.00065754	1.7
280.0	0.0017316	1.4	0.0010189	1.6	0.00060352	1.7
285.0	0.0016153	1.4	0.00094294	1.5	0.0005547	1.7
290.0	0.0015087	1.4	0.00087373	1.5	0.00051051	1.6
295.0	0.0014107	1.3	0.00081063	1.5	0.00047047	1.6
300.0	0.0013207	1.3	0.00075301	1.5	0.00043412	1.6

R/T characteristics

R/T No.	8415							
T (°C)	B _{0/100} = 3970 K		T (°C)	B _{0/100} = 3970 K		T (°C)	B _{0/100} = 3970 K	
	R _T /R ₂₅	α (%/K)		R _T /R ₂₅	α (%/K)		R _T /R ₂₅	α (%/K)
−55.0	103.29	7.6	65.0	0.20682	3.5	185.0	0.0085294	2.0
−50.0	71.079	7.3	70.0	0.17389	3.4	190.0	0.0077229	2.0
−45.0	49.619	7.1	75.0	0.14687	3.3	195.0	0.0070067	1.9
−40.0	35.108	6.8	80.0	0.12459	3.2	200.0	0.0063691	1.9
−35.0	25.158	6.5	85.0	0.10614	3.2	205.0	0.0058005	1.9
−30.0	18.245	6.3	90.0	0.09078	3.1	210.0	0.0052924	1.8
−25.0	13.383	6.1	95.0	0.077949	3.0	215.0	0.0048373	1.8
−20.0	9.9221	5.9	100.0	0.067183	2.9	220.0	0.004429	1.7
−15.0	7.4316	5.7	105.0	0.058113	2.9	225.0	0.004062	1.7
−10.0	5.6202	5.5	110.0	0.050443	2.8	230.0	0.0037315	1.7
−5.0	4.2894	5.3	115.0	0.043932	2.7	235.0	0.0034333	1.6
0.0	3.3024	5.2	120.0	0.038386	2.7	240.0	0.0031639	1.6
5.0	2.5607	5.0	125.0	0.033645	2.6	245.0	0.00292	1.6
10.0	2.0017	4.8	130.0	0.029579	2.5	250.0	0.0026988	1.6
15.0	1.5768	4.7	135.0	0.02608	2.5	255.0	0.002498	1.5
20.0	1.2513	4.6	140.0	0.02306	2.4	260.0	0.0023153	1.5
25.0	1.0000	4.4	145.0	0.020446	2.4	265.0	0.0021489	1.5
30.0	0.80451	4.3	150.0	0.018176	2.3	270.0	0.0019971	1.5
35.0	0.65139	4.2	155.0	0.016199	2.3	275.0	0.0018584	1.4
40.0	0.53064	4.0	160.0	0.014473	2.2	280.0	0.0017316	1.4
45.0	0.43481	3.9	165.0	0.012962	2.2	285.0	0.0016153	1.4
50.0	0.35828	3.8	170.0	0.011636	2.1	290.0	0.0015087	1.4
55.0	0.29681	3.7	175.0	0.010469	2.1	295.0	0.0014107	1.3
60.0	0.24715	3.6	180.0	0.0094395	2.0	300.0	0.0013207	1.3

Mounting instructions

1 Soldering

1.1 Leaded NTC thermistors

Leaded thermistors comply with the solderability requirements specified by CECC.

When soldering, care must be taken that the NTC thermistors are not damaged by excessive heat. The following maximum temperatures, maximum time spans and minimum distances have to be observed:

	<i>Dip soldering</i>	<i>Iron soldering</i>
Bath temperature	max. 260 °C	max. 360 °C
Soldering time	max. 4 s	max. 2 s
Distance from thermistor	min. 6 mm	min. 6 mm

Under more severe soldering conditions the resistance may change.

1.2 Leadless NTC thermistors

In case of NTC thermistors without leads, soldering is restricted to devices which are provided with a solderable metallization. The temperature shock caused by the application of hot solder may produce fine cracks in the ceramic, resulting in changes in resistance.

To prevent leaching of the metallization, solder with silver additives or with a low tin content should be used. In addition, soldering methods should be employed which permit short soldering times.

2 Clamp contacting

Pressure contacting by means of clamps is particularly suitable for applications involving frequent switching and high turn-on powers.

3 Robustness of terminations (leaded types)

The leads meet the requirements of IEC 60068-2-21. They may not be bent closer than 4 mm from the solder joint on the thermistor body or from the point at which they leave the feed-throughs. During bending, any mechanical stress at the outlet of the leads must be removed. The bending radius should be at least 0.75 mm.

Tensile strength: Test Ua1:

Leads	$\varnothing \leq 0.25 \text{ mm}$	=	1.0 N
	$0.25 < \varnothing \leq 0.35 \text{ mm}$	=	2.5 N
	$0.35 < \varnothing \leq 0.50 \text{ mm}$	=	5.0 N
	$0.50 < \varnothing \leq 0.80 \text{ mm}$	=	10.0 N
	$0.80 < \varnothing \leq 1.25 \text{ mm}$	=	20.0 N

Temperature measurement	B57550G, B57550G1
Glass-encapsulated sensors	G550/G1550

Bending strength: Test Ub:

Two 90°-bends in opposite directions at a weight of 0.25 kg.

Torsional strength: Test Uc: severity 2

The lead is bent by 90° at a distance of 6 to 6.5 mm from the thermistor body.

The bending radius of the leads should be approx. 0.75 mm. Two torsions of 180° each (severity 2).

When subjecting leads to mechanical stress, the following should be observed:

Tensile stress on leads

During mounting and operation tensile forces on the leads are to be avoided.

Bending of leads

Bending of the leads directly on the thermistor body is not permissible.

A lead may be bent at a minimum distance of twice the wire's diameter +2 mm from the solder joint on the thermistor body. During bending the wire must be mechanically relieved at its outlet. The bending radius should be at least 0.75 mm.

Twisting of leads

The twisting (torsion) by 180° of a lead bent by 90° is permissible at 6 mm from the bottom of the thermistor body.

4 Sealing and potting

When thermistors are sealed, potted or overmolded, there must be no mechanical stress caused by thermal expansion during the production process (curing / overmolding process) and during later operation. The upper category temperature of the thermistor must not be exceeded. Ensure that the materials used (sealing / potting compound and plastic material) are chemically neutral.

5 Cleaning

If cleaning is necessary, mild cleaning agents such as ethyl alcohol and cleaning gasoline are recommended. Cleaning agents based on water are not allowed. Ultrasonic cleaning methods are permissible.

6 Storage

In order to maintain their solderability, thermistors must be stored in a non-corrosive atmosphere. Humidity, temperature and container materials are critical factors.

Do not store SMDs where they are exposed to heat or direct sunlight. Otherwise, the packing material may be deformed or SMDs may stick together, causing problems during mounting. After opening the factory seals, such as polyvinyl-sealed packages, use the SMDs as soon as possible.

Temperature measurement**B57550G, B57550G1****Glass-encapsulated sensors****G550/G1550**

The components should be left in the original packing. Touching the metallization of unsoldered thermistors may change their soldering properties.

Storage temperature: $-25\text{ }^{\circ}\text{C}$ up to $45\text{ }^{\circ}\text{C}$

Relative humidity (without condensation): $\leq 75\%$ annual mean

$< 95\%$, maximum 30 days per annum

Solder the thermistors listed in this data book after shipment from EPCOS within the time specified:

SMDs: 12 months

Leaded components: 24 months

Cautions and warnings General

See "Important notes" at the end of this document.

Storage

- Store thermistors only in original packaging. Do not open the package prior to storage.
- Storage conditions in original packaging: storage temperature $-25\text{ }^{\circ}\text{C} \dots +45\text{ }^{\circ}\text{C}$, relative humidity $\leq 75\%$ annual mean, $<95\%$ maximum 30 days per annum, dew precipitation is inadmissible.
- Do not store thermistors where they are exposed to heat or direct sunlight. Otherwise, the packing material may be deformed or components may stick together, causing problems during mounting.
- Avoid contamination of thermistor surface during storage, handling and processing.
- Avoid storage of thermistors in harmful environments like corrosive gases (SO_x , Cl etc).
- Use the components as soon as possible after opening the factory seals, i.e. the polyvinyl-sealed packages.
- Solder thermistors within the time specified after shipment from EPCOS.
For leaded components this is 24 months, for SMDs 12 months.

Handling

- NTC thermistors must not be dropped. Chip-offs or any other damage must not be caused during handling of NTCs.
- Do not touch components with bare hands. Gloves are recommended.
- Avoid contamination of thermistor surface during handling.

Bending / twisting leads

- A lead (wire) may be bent at a minimum distance of twice the wire's diameter plus 4 mm from the component head or housing. When bending ensure the wire is mechanically relieved at the component head or housing. The bending radius should be at least 0.75 mm.
- Twisting (torsion) by 180° of a lead bent by 90° is permissible at 6 mm from the bottom of the thermistor body.

Soldering

- Use resin-type flux or non-activated flux.
- Insufficient preheating may cause ceramic cracks.
- Rapid cooling by dipping in solvent is not recommended.
- Complete removal of flux is recommended.

Mounting

- Ensure that no thermo-mechanical stress occurs due to production processes (curing or overmolding processes) when thermistors are sealed, potted or overmolded or during their subsequent operation. The maximum temperature of the thermistor must not be exceeded. Ensure that the materials used (sealing/potting compound and plastic material) are chemically neutral.
- Electrodes/contacts must not be scratched or damaged before/during/after the mounting process.
- Contacts and housing used for assembly with the thermistor must be clean before mounting.
- Ensure that adjacent materials are designed for operation at temperatures comparable to the surface temperature of the thermistor. Be sure that surrounding parts and materials can withstand the temperature.
- Avoid contamination of the thermistor surface during processing.
- The connections of sensors (e.g. cable end, wire end, plug terminal) may only be exposed to an environment with normal atmospheric conditions.
- Tensile forces on cables or leads must be avoided during mounting and operation.
- Bending or twisting of cables or leads directly on the thermistor body is not permissible.
- Avoid using chemical substances as mounting aids. It must be ensured that no water or other liquids enter the NTC thermistors (e.g. through plug terminals). In particular, water based substances (e.g. soap suds) must not be used as mounting aids for sensors.

Operation

- Use thermistors only within the specified operating temperature range.
- Use thermistors only within the specified power range.
- Environmental conditions must not harm the thermistors. Only use the thermistors under normal atmospheric conditions or within the specified conditions.
- Contact of NTC thermistors with any liquids and solvents should be prevented. It must be ensured that no water enters the NTC thermistors (e.g. through plug terminals). For measurement purposes (checking the specified resistance vs. temperature), the component must not be immersed in water but in suitable liquids (e.g. Galden).
- Avoid dewing and condensation unless thermistor is specified for these conditions.
- Bending or twisting of cables and/or wires is not permissible during operation of the sensor in the application.
- Be sure to provide an appropriate fail-safe function to prevent secondary product damage caused by malfunction.

This listing does not claim to be complete, but merely reflects the experience of EPCOS AG.

Symbols and terms

Symbol	English	German
A	Area	Fläche
AWG	American Wire Gauge	Amerikanische Norm für Drahtquerschnitte
B	B value	B-Wert
B _{25/100}	B value determined by resistance measurement at 25 °C and 100 °C	B-Wert, ermittelt durch Widerstandsmessungen bei 25 °C und 100 °C
C _{th}	Heat capacitance	Wärmekapazität
I	Current	Strom
N	Number (integer)	Anzahl (ganzzahliger Wert)
P ₂₅	Maximum power at 25 °C	Maximale Leistung bei 25 °C
P _{diss}	Power dissipation	Verlustleistung
P _{el}	Electrical power	Elektrische Leistung
P _{max}	Maximum power within stated temperature range	Maximale Leistung im angegebenen Temperaturbereich
ΔR _B /R _B	Resistance tolerance caused by spread of B value	Widerstandstoleranz, die durch die Streuung des B-Wertes verursacht wird
R _{ins}	Insulation resistance	Isolationswiderstand
R _p	Parallel resistance	Parallelwiderstand
R _R	Rated resistance	Nennwiderstand
ΔR _R /R _R	Resistance tolerance	Widerstandstoleranz
R _S	Series resistance	Serienwiderstand
R _T	Resistance at temperature T (e.g. R ₂₅ = resistance at 25 °C)	Widerstand bei Temperatur T (z.B. R ₂₅ = Widerstand bei 25 °C)
T	Temperature	Temperatur
ΔT	Temperature tolerance	Temperaturtoleranz
t	Time	Zeit
T _A	Ambient temperature	Umgebungstemperatur
T _{max}	Upper category temperature	Obere Grenztemperatur (Kategorietemperatur)
T _{min}	Lower category temperature	Untere Grenztemperatur (Kategorietemperatur)
T _{op}	Operating temperature	Betriebstemperatur
T _R	Rated temperature	Nenntemperatur
T _{surf}	Surface temperature	Oberflächentemperatur
V	Voltage	Spannung
V _{ins}	Insulation test voltage	Isolationsprüfspannung
V _{op}	Operating voltage	Betriebsspannung
V _{test}	Test voltage	Prüfspannung

Temperature measurement	B57550G, B57550G1
Glass-encapsulated sensors	G550/G1550

Symbol	English	German
α	Temperature coefficient	Temperaturkoeffizient
Δ	Tolerance, change	Toleranz, Änderung
δ_{th}	Dissipation factor	Wärmeleitwert
τ_c	Thermal cooling time constant	Thermische Abkühlzeitkonstante
τ_a	Thermal time constant	Thermische Zeitkonstante

Abbreviations / Notes

Symbol	English	German
<u>SMD</u>	Surface-mounted devices	Oberflächenmontierbares Bauelement
*	To be replaced by a number in ordering codes, type designations etc.	Platzhalter für Zahl im Bestellnummern-code oder für die Typenbezeichnung.
+	To be replaced by a letter. All dimensions are given in mm. The commas used in numerical values denote decimal points.	Platzhalter für einen Buchstaben. Alle Maße sind in mm angegeben. Verwendete Kommas in Zahlenwerten bezeichnen Dezimalpunkte.

Important notes

The following applies to all products named in this publication:

1. Some parts of this publication contain **statements about the suitability of our products for certain areas of application**. These statements are based on our knowledge of typical requirements that are often placed on our products in the areas of application concerned. We nevertheless expressly point out **that such statements cannot be regarded as binding statements about the suitability of our products for a particular customer application**. As a rule we are either unfamiliar with individual customer applications or less familiar with them than the customers themselves. For these reasons, it is always ultimately incumbent on the customer to check and decide whether a product with the properties described in the product specification is suitable for use in a particular customer application.
2. We also point out that **in individual cases, a malfunction of electronic components or failure before the end of their usual service life cannot be completely ruled out in the current state of the art, even if they are operated as specified**. In customer applications requiring a very high level of operational safety and especially in customer applications in which the malfunction or failure of an electronic component could endanger human life or health (e.g. in accident prevention or life-saving systems), it must therefore be ensured by means of suitable design of the customer application or other action taken by the customer (e.g. installation of protective circuitry or redundancy) that no injury or damage is sustained by third parties in the event of malfunction or failure of an electronic component.
3. **The warnings, cautions and product-specific notes must be observed.**
4. In order to satisfy certain technical requirements, **some of the products described in this publication may contain substances subject to restrictions in certain jurisdictions (e.g. because they are classed as hazardous)**. Useful information on this will be found in our Material Data Sheets on the Internet (www.tdk-electronics.tdk.com/material). Should you have any more detailed questions, please contact our sales offices.
5. We constantly strive to improve our products. Consequently, **the products described in this publication may change from time to time**. The same is true of the corresponding product specifications. Please check therefore to what extent product descriptions and specifications contained in this publication are still applicable before or when you place an order.

We also **reserve the right to discontinue production and delivery of products**. Consequently, we cannot guarantee that all products named in this publication will always be available. The aforementioned does not apply in the case of individual agreements deviating from the foregoing for customer-specific products.
6. Unless otherwise agreed in individual contracts, **all orders are subject to our General Terms and Conditions of Supply**.
7. **Our manufacturing sites serving the automotive business apply the IATF 16949 standard**. The IATF certifications confirm our compliance with requirements regarding the quality management system in the automotive industry. Referring to customer requirements and customer specific requirements ("CSR") TDK always has and will continue to have the policy of respecting individual agreements. Even if IATF 16949 may appear to support the acceptance of unilateral requirements, we hereby like to emphasize that **only requirements mutually agreed upon can and will be implemented in our Quality Management System**. For clarification purposes we like to point out that obligations from IATF 16949 shall only become legally binding if individually agreed upon.
8. The trade names EPCOS, CeraCharge, CeraDiode, CeraLink, CeraPad, CeraPlas, CSMP, CTVS, DeltaCap, DigiSiMic, ExoCore, FilterCap, FormFit, LeaXield, MiniBlue, MiniCell, MKD, MKK, MotorCap, PCC, PhaseCap, PhaseCube, PhaseMod, PhiCap, PowerHap, PQSine, PQvar, SIFERRIT, SIFI, SIKOREL, SilverCap, SIMDAD, SiMic, SIMID, SineFormer, SIOV, ThermoFuse, WindCap are **trademarks registered or pending** in Europe and in other countries. Further information will be found on the Internet at www.tdk-electronics.tdk.com/trademarks.